

EPG65

HIGH STRENGTH EPOXY INJECTION SYSTEM



FEATURES

- High load capacity for wide range of base material.
- Suitable for close edge and close anchor spacing.
- Suitable for cored and oversized holes.
- Low shrinkage and low chemical wastages.
- Extended working time ideally for tropical climate.
- Ideal for damp hole application.

APPLICATIONS

- Post-installed rebar connections.
- Shear connector applications.
- Strutting and wall barriers extensions.
- Structural steel-to-concrete connections.
- Stud rods fixings up to M30 in diameter.

SHELF LIFE

- Cartridges should be stored in their original packaging in cool conditions (+5°C ~ +25°C) out of direct sunlight. When stored in this condition, the shelf life will be 18 months from the date of manufacture.

RANGE OF CONCRETE QUALITY

C20/25 ~ C50/60

RANGE OF LOADING

5.1 kN ~ 128.0 kN (SWL)



Heavy loads

HOLE ORIENTATION



BASE MATERIALS



Concrete









Concrete block
solid stone

VA RODS AVAILABILITY



► ORDERING DETAILS

PRODUCT DESCRIPTION	PACKING CONTENT (PCs.)	PRODUCT PART NO.	
EPG65 - 650ml (Dual Cartridge System)	10	EPG65	
Applicator Handgun - 650ml (For 600~650ml Cartridges)	1	GZ65	
Applicator Battery Handgun - 650ml (For 600~650ml Cartridges)	1	GZ65B	
Mixing Nozzle - 255mm Mixing Nozzle Long - 370mm	Bulk Bulk	NZ65 NZ65L	
Hole Blower	1	HCP	
Hole Cleaning Brush Cleaning Brush - 10mm Cleaning Brush - 12mm Cleaning Brush - 18mm Cleaning Brush - 28mm	1 1 1 1	CB10 CB12 CB18 CB28	

VA CHEMICAL STUD RODS - STEEL CLASS 5.8 ZINC GALVANISED

PRODUCT DESCRIPTION	FIXTURE HOLE DIAMETER (mm)	MAX. FIXTURE THICKNESS (mm)	PACKING CONTENT (PCs.)	PRODUCT PART NO.
M8 x 110mm	9	15	10	VA8110
M10 x 130mm	12	20	10	VA10130
M12 x 160mm	14	30	10	VA12160
M16 x 190mm	18	40	10	VA16190
M20 x 260mm	22	50	6	VA20260
M24 x 300mm	28	55	6	VA24300



VA CHEMICAL STUD RODS - STEEL CLASS 5.8 HOT-DIPPED GALVANISED

PRODUCT DESCRIPTION	FIXTURE HOLE DIAMETER (mm)	MAX. FIXTURE THICKNESS (mm)	PACKING CONTENT (PCs.)	PRODUCT PART NO.
M8 x 110mm	9	15	10	VA8110GH
M10 x 130mm	12	20	10	VA10130GH
M12 x 160mm	14	30	10	VA12160GH
M16 x 190mm	18	40	10	VA16190GH
M20 x 260mm	22	50	6	VA20260GH
M24 x 300mm	28	55	6	VA24300GH



VAH CHEMICAL STUD RODS - STEEL CLASS 8.8 ZINC GALVANISED

PRODUCT DESCRIPTION	FIXTURE HOLE DIAMETER (mm)	MAX. FIXTURE THICKNESS (mm)	PACKING CONTENT (PCs.)	PRODUCT PART NO.
M8 x 110mm	9	15	10	VAH8110
M10 x 130mm	12	20	10	VAH10130
M12 x 160mm	14	30	10	VAH12160
M16 x 190mm	18	40	10	VAH16190
M20 x 260mm	22	50	6	VAH20260
M24 x 300mm	28	55	6	VAH24300



VAH CHEMICAL STUD RODS - STEEL CLASS 8.8 HOT-DIPPED GALVANISED

PRODUCT DESCRIPTION	FIXTURE HOLE DIAMETER (mm)	MAX. FIXTURE THICKNESS (mm)	PACKING CONTENT (PCs.)	PRODUCT PART NO.
M8 x 110mm	9	15	10	VAH8110GH
M10 x 130mm	12	20	10	VAH10130GH
M12 x 160mm	14	30	10	VAH12160GH
M16 x 190mm	18	40	10	VAH16190GH
M20 x 260mm	22	50	6	VAH20260GH
M24 x 300mm	28	55	6	VAH24300GH



G

VAR CHEMICAL STUD RODS - STAINLESS STEEL CLASS 304 (A2)

PRODUCT DESCRIPTION	FIXTURE HOLE DIAMETER (mm)	MAX. FIXTURE THICKNESS (mm)	PACKING CONTENT (PCs.)	PRODUCT PART NO.
M8 x 110mm	9	15	10	VAR8110
M10 x 130mm	12	20	10	VAR10130
M12 x 160mm	14	30	10	VAR12160
M16 x 190mm	18	40	10	VAR16190
M20 x 260mm	22	50	6	VAR20260
M24 x 300mm	28	55	6	VAR24300



A2
INOX

VAS CHEMICAL STUD RODS - STAINLESS STEEL CLASS 316 (A4)

PRODUCT DESCRIPTION	FIXTURE HOLE DIAMETER (mm)	MAX. FIXTURE THICKNESS (mm)	PACKING CONTENT (PCs.)	PRODUCT PART NO.
M8 x 110mm	9	15	10	VAS8110
M10 x 130mm	12	20	10	VAS10130
M12 x 160mm	14	30	10	VAS12160
M16 x 190mm	18	40	10	VAS16190
M20 x 260mm	22	50	6	VAS20260
M24 x 300mm	28	55	6	VAS24300



A4
INOX

* Stud rod diameter larger than M27 and above are made-to-order or on indent basis.

► INSTALLATION PERIMETER & LOADING DATA

EPG65 WITH VA (STEEL CLASS 5.8) RODS - ZINC GALVANISED & HOT DIPPED GALVANISED

ANCHOR SIZE	HOLE DIAMETER (mm)	ANCHORAGE DEPTH (mm)	MINIMUM CONCRETE THICKNESS (mm)	TIGHTENING TORQUE (Nm)	RECOMMENDED SPACING & EDGE DISTANCE TO FULL LOAD (mm)		ABSOLUTE MINIMUM SPACING & EDGE DISTANCE (mm)		RECOMMENDED LOAD ¹ (kN)	
					TENSION	SHEAR	TENSION	SHEAR	TENSION	SHEAR
M8	10	80	110	10	160	80	40	40	8.6	5.1
M10	12	90	120	20	180	90	45	45	12.1	8.6
M12	14	110	140	40	220	110	55	55	17.8	12.0
M16	18	125	155	80	250	125	65	65	22.9	22.3
M20	24	170	220	120	340	170	85	85	37.1	34.9
M24	28	210	270	200	420	210	105	105	49.9	50.3
M27	30	250	310	240	500	250	125	125	69.9	65.7
M30	35	270	340	270	540	270	135	135	84.1	80.0

¹ Loading based on non-cracked concrete, $f_{ck,cube} = 25 \text{ N/mm}^2$ (C20/25).

EPG65 WITH VAH (STEEL CLASS 8.8) RODS - ZINC GALVANISED & HOT DIPPED GALVANISED

ANCHOR SIZE	HOLE DIAMETER (mm)	ANCHORAGE DEPTH (mm)	MINIMUM CONCRETE THICKNESS (mm)	TIGHTENING TORQUE (Nm)	RECOMMENDED SPACING & EDGE DISTANCE TO FULL LOAD (mm)		ABSOLUTE MINIMUM SPACING & EDGE DISTANCE (mm)		RECOMMENDED LOAD ¹ (kN)	
					TENSION	SHEAR	TENSION	SHEAR	TENSION	SHEAR
M8	10	80	110	10	160	80	40	40	8.6	8.6
M10	12	90	120	20	180	90	45	45	12.1	13.1
M12	14	110	140	40	220	110	55	55	17.8	19.4
M16	18	125	155	80	250	125	65	65	22.9	36.0
M20	24	170	220	150	340	170	85	85	37.1	56.0
M24	28	210	270	200	420	210	105	105	49.9	80.6
M27	30	250	310	240	500	250	125	125	69.9	105.1
M30	35	270	340	270	540	270	135	135	84.1	128.0

¹ Loading based on non-cracked concrete, $f_{ck,cube} = 25 \text{ N/mm}^2$ (C20/25).

EPG650 WITH VAR & VAS (STAINLESS STEEL) RODS - CLASS 304 (A2) & CLASS 316 (A4)


ANCHOR SIZE	HOLE DIAMETER (mm)	ANCHORAGE DEPTH (mm)	MINIMUM CONCRETE THICKNESS (mm)	TIGHTENING TORQUE (Nm)	RECOMMENDED SPACING & EDGE DISTANCE TO FULL LOAD (mm)		ABSOLUTE MINIMUM SPACING & EDGE DISTANCE (mm)		RECOMMENDED LOAD ¹ (kN)	
					TENSION	SHEAR	TENSION	SHEAR	TENSION	SHEAR
M8	10	80	110	10	160	80	40	40	8.6	6.0
M10	12	90	120	20	180	90	45	45	12.1	9.2
M12	14	110	140	40	220	110	55	55	17.8	13.7
M16	18	125	155	80	250	125	65	65	22.9	25.2
M20	24	170	220	150	340	170	85	85	37.1	39.4
M24	28	210	270	200	420	210	105	105	49.9	56.8
M27	30	250	310	240	500	250	125	125	69.9	73.7
M30	35	270	340	270	540	270	135	135	84.1	89.7

¹ Loading based on non-cracked concrete, $f_{ck,cube} = 25 \text{ N/mm}^2$ (C20/25).

GEL AND CURING TIME^{1,2}

BASE MATERIAL TEMPERATURE $T_{\text{base material}} (\text{°C})$	GEL TIME (WORKING TIME) $t_{\text{gel}} (\text{mins})$	CURING TIME $t_{\text{cure}} (\text{hrs})$
$+10 \leq T_{\text{base material}} < +20$	60	12
$+20 \leq T_{\text{base material}} < +30$	15	7
$+30 \leq T_{\text{base material}} < +40$	7	5
Above +40	4	3


Note: If during the installation of the rod the temperature drop below -6°C or rises above 60°C , please contact our Engineers for the proper procedures.




¹ Cartridge should be $\geq +10^{\circ}\text{C}$.

² The curing time are for dry base material only. In wet base material, the curing time must be doubled.

SETTING DIAGRAM



INSTALLATION PROCEDURE



EPG65 HIGH STRENGTH EPOXY FOR POST-INSTALLED REBAR APPLICATIONS
(Design Load Approach with BS8110 Bond Strength Method)

Concrete Compressive Strength: $f_{ck,cube} = 25 \text{ N/mm}^2$


Rebar Size, d_s	$\phi 10$	$\phi 12$	$\phi 16$	$\phi 20$	$\phi 25$	$\phi 32$	$\phi 40$						
Design Steel Resistance, $N_{Rd,s}$ [kN]	31.4	45.2	80.4	125.7	196.4	321.7	502.7						
Design Bond Stress, τ_{Rd} [N/mm ²]	7.2	7.8	8.1	7.3	7.3	7.3	7.2						
Drilled Hole Diameter, d_o [mm]	13 ~ 14	15 ~ 16	20 ~ 22	25 ~ 28	30 ~ 32	40 ~ 42	50 ~ 52						
Bar Spacing, s [mm]	50	65	80	100	125	160	200						
Edge Distance, c [mm]	40	40	40	50	65	80	100						
$L_{b,reqd} / \text{Rebar } \phi$	14	13	12	14	14	14	14						
Anchorage Length, L_b [mm]	Design Tensile Bonding Capacity, N_{Rd} [kN]												
100	22.6	<i>"Minimum depth to develop full steel shear"</i>											
120	27.1							35.3					
140	31.4							41.2					
160								45.2	65.2				
175									71.3				
200									80.4	91.7			
225										103.2			
250										114.7	143.4		
275										125.7	157.7		
320											183.5	234.9	
345											196.4	253.2	
400												293.6	362.0
440												321.7	398.2
560													502.7
Length to Develop Steel Yield, $L_{b,reqd}$ [mm]	139							154	197	274	343	438	556

- 1) Safety factor for design tensile steel resistance: $\gamma_{Ms,N} = 1.15$ (based on steel yield strength of 460 N/mm²).
- 2) Safety factor for design tensile pull-out resistance: $\gamma_{Mc,N} = 1.8$
- 3) Loading applicable to non-cracked concrete with design comply in accordance to BS8110.
- 4) Safety factor for design tensile concrete cone resistance: $\gamma_{Mc,N} = 1.5$
- 5) Minimum spacing shall be $4d_s$ bar to bar or $5d_s$ centre-to-centre.
- 6) Minimum edge distance shall be $2d_s$ bar to bar or $2.5d_s$ centre-to-centre.

TEST CERTIFICATIONS

- 1) Tested to SIRIM QAS to BS 5950 Part 1 for studs and rebars.


SUGGESTED APPLICATIONS




Overlap joints for slabs and beams or foundation column or wall; rebar connection for simply supported slabs or beams; shear connector or compression component joints.

Important note: Architect or design engineer must conduct final checked with the actual site condition for any variations against tabulated data.

SETTING DIAGRAM



INSTALLATION PROCEDURE



EPG65 HIGH STRENGTH EPOXY FOR POST-INSTALLED REBAR APPLICATIONS
(Design Load Approach with BS8110 Bond Strength Method)

Concrete Compressive Strength: $f_{ck,cube} = 30 \text{ N/mm}^2$

Rebar Size, d_s	$\phi 10$	$\phi 12$	$\phi 16$	$\phi 20$	$\phi 25$	$\phi 32$	$\phi 40$
Design Steel Resistance, $N_{Rd,s}$ [kN]	31.4	45.2	80.4	125.7	196.4	321.7	502.7
Design Bond Stress, τ_{Rd} [N/mm ²]	7.3	8.0	8.3	7.4	7.4	7.4	7.3
Drilled Hole Diameter, d_o [mm]	13 ~ 14	15 ~ 16	20 ~ 22	25 ~ 28	30 ~ 32	40 ~ 42	50 ~ 52
Bar Spacing, s [mm]	50	65	80	100	125	160	200
Edge Distance, c [mm]	40	40	40	50	65	80	100
$L_{b,reqd} / \text{Rebar } \phi$	14	13	12	13	13	13	14
Anchorage Length, L_b [mm]	Design Tensile Bonding Capacity, N_{Rd} [kN]						
100	23.1						
120	27.7	36.0					
140	31.4	42.0					
160		45.2	66.5				
180			74.8				
200			80.4	93.6			
250				117.0	146.2		
270				125.7	157.9		
320					187.2	239.6	
340					196.4	254.5	
400						299.5	369.2
430						321.7	396.9
550							502.7
Length to Develop Steel Yield, $L_{b,reqd}$ [mm]	136	151	194	269	336	430	545


"Minimum depth to develop full steel shear"

- 1) Safety factor for design tensile steel resistance: $\gamma_{Ms,N} = 1.15$ (based on steel yield strength of 460 N/mm²).
- 2) Safety factor for design tensile pull-out resistance: $\gamma_{Mc,N} = 1.8$
- 3) Loading applicable to non-cracked concrete with design comply in accordance to BS8110.
- 4) Safety factor for design tensile concrete cone resistance: $\gamma_{Mc,N} = 1.5$
- 5) Minimum spacing shall be $4d_s$ bar to bar or $5d_s$ centre-to-centre.
- 6) Minimum edge distance shall be $2d_s$ bar to bar or $2.5d_s$ centre-to-centre.

TEST CERTIFICATIONS

- 1) Tested to SIRIM QAS to BS 5950 Part 1 for studs and rebars.


SUGGESTED APPLICATIONS




Overlap joints for slabs and beams or foundation column or wall; rebar connection for simply supported slabs or beams; shear connector or compression component joints.

Important note: Architect or design engineer must conduct final checked with the actual site condition for any variations against tabulated data.

SETTING DIAGRAM



INSTALLATION PROCEDURE



EPG65 HIGH STRENGTH EPOXY FOR POST-INSTALLED REBAR APPLICATIONS
(Design Load Approach with BS8110 Bond Strength Method)

Concrete Compressive Strength: $f_{ck,cube} = 35 \text{ N/mm}^2$


Rebar Size, d_s	$\phi 10$	$\phi 12$	$\phi 16$	$\phi 20$	$\phi 25$	$\phi 32$	$\phi 40$						
Design Steel Resistance, $N_{Rd,s}$ [kN]	31.4	45.2	80.4	125.7	196.4	321.7	502.7						
Design Bond Stress, τ_{Rd} [N/mm ²]	7.4	8.1	8.4	7.5	7.5	7.5	7.4						
Drilled Hole Diameter, d_o [mm]	13 ~ 14	15 ~ 16	20 ~ 22	25 ~ 28	30 ~ 32	40 ~ 42	50 ~ 52						
Bar Spacing, s [mm]	50	65	80	100	125	160	200						
Edge Distance, c [mm]	40	40	40	50	65	80	100						
$L_{b,reqd} / \text{Rebar } \phi$	13	12	12	13	13	13	13						
Anchorage Length, L_b [mm]	Design Tensile Bonding Capacity, N_{Rd} [kN]												
100	23.4	<i>"Minimum depth to develop full steel shear"</i>											
120	28.1							36.5					
140	31.4							42.6					
160								45.2	67.4				
180									75.8				
200									80.4	94.9			
250										118.6	148.3		
265										125.7	157.2		
320											189.8	242.9	
335											196.4	254.3	
400												303.6	374.3
425												321.7	397.7
500													467.9
540													502.7
Length to Develop Steel Yield, $L_{b,reqd}$ [mm]	134							149	191	265	331	424	537

- 1) Safety factor for design tensile steel resistance: $\gamma_{Ms,N} = 1.15$ (based on steel yield strength of 460 N/mm²).
- 2) Safety factor for design tensile pull-out resistance: $\gamma_{Mc,N} = 1.8$
- 3) Loading applicable to non-cracked concrete with design comply in accordance to BS8110.
- 4) Safety factor for design tensile concrete cone resistance: $\gamma_{Mc,N} = 1.5$
- 5) Minimum spacing shall be $4d_s$ bar to bar or $5d_s$ centre-to-centre.
- 6) Minimum edge distance shall be $2d_s$ bar to bar or $2.5d_s$ centre-to-centre.

TEST CERTIFICATIONS

- 1) Tested to SIRIM QAS to BS 5950 Part 1 for studs and rebars.


SUGGESTED APPLICATIONS




Overlap joints for slabs and beams or foundation column or wall; rebar connection for simply supported slabs or beams; shear connector or compression component joints.

Important note: Architect or design engineer must conduct final checked with the actual site condition for any variations against tabulated data.

SETTING DIAGRAM



INSTALLATION PROCEDURE



EPG65 HIGH STRENGTH EPOXY FOR POST-INSTALLED REBAR APPLICATIONS
(Design Load Approach with BS8110 & ACI 318 Concrete Splitting Criteria)

Concrete Compressive Strength: $f_{ck,cube} = 25 \text{ N/mm}^2$


Rebar Size, d_s		$\phi 10$	$\phi 12$	$\phi 16$	$\phi 20$	$\phi 25$	$\phi 32$	$\phi 40$						
Design Steel Resistance, $N_{Rd,s}$	[kN]	34.4	49.6	88.1	137.6	215.1	352.4	550.6						
Splitting Bond Stress, $\tau_{sp,d}$	[N/mm ²]	3.49	3.49	3.49	3.25	2.80	2.80	2.80						
Drilled Hole Diameter, d_o	[mm]	13 ~ 14	15 ~ 16	20 ~ 22	25 ~ 28	30 ~ 32	40 ~ 42	50 ~ 52						
Bar Spacing, s	[mm]	50	60	80	100	125	160	200						
Edge Distance, c	[mm]	40	40	40	50	65	80	100						
$L_{b,req} / \text{Rebar } \phi$		31	31	31	34	39	39	39						
Anchorage Length, L_b [mm]		Design Tensile Pull-Out / Concrete Cone Resistance, N_{rd} [kN]												
100	11.0	"Minimum depth to develop full steel shear"												
120	13.2								15.8					
160	17.5								21.1	28.1				
200	21.9								26.3	35.1	40.8			
250	27.4								32.9	43.9	51.1	55.0		
300	32.9								39.5	52.6	61.3	66.0		
320	34.4								42.1	56.1	65.4	70.4	90.1	
400									49.6	70.2	81.7	88.0	112.6	140.8
450										79.0	91.9	99.0	126.7	158.4
500										88.1	102.1	110.0	140.8	176.0
600				122.5	132.0	168.9	211.1							
675				137.6	148.5	190.0	237.5							
750					165.0	211.1	263.9							
980					215.1	275.9	344.9							
1000						281.5	351.9							
1250						352.4	439.9							
1400							492.7							
1565							550.6							
Length to Develop Steel Yield, $L_{b,req}$ [mm]		314	377	502	674	978	1,252	1,565						

- 1) Design tensile steel resistance: $N_{Rd,s} = f_y * A_s / \gamma_{Ms,N}$ where $\gamma_{Ms,N} = 1.05$ (based on steel yield of 460 N/mm²).
- 2) Design value complied in accordance to BS8110 and ACI 318 concrete splitting criteria.
- 3) Minimum spacing shall be $4d_s$ bar to bar or $5d_s$ centre-to-centre.
- 4) Minimum edge distance shall be $2d_s$ bar to bar or $2.5d_s$ centre-to-centre.
- 5) Applicable to dry and wet concrete application.
- 6) Design value based on non-cracked concrete.

TEST CERTIFICATIONS


- 1) Tested to SIRIM QAS to BS 5950 Part 1 for studs and rebars.

SUGGESTED APPLICATIONS




Overlap joints for slabs and beams or foundation column or wall; rebar connection for simply supported slabs or beams; shear connector or compression component joints.
Important note: Architect or design engineer must conduct final checked with the actual site condition for any variations against tabulated data.

SETTING DIAGRAM



INSTALLATION PROCEDURE



EPG65 HIGH STRENGTH EPOXY FOR POST-INSTALLED REBAR APPLICATIONS

(Design Load Approach with BS8110 & ACI 318 Concrete Splitting Criteria)

Concrete Compressive Strength: $f_{ck,cube} = 30 \text{ N/mm}^2$


Rebar Size, d_s		$\phi 10$	$\phi 12$	$\phi 16$	$\phi 20$	$\phi 25$	$\phi 32$	$\phi 40$
Design Steel Resistance, $N_{Rd,s}$	[kN]	34.4	49.6	88.1	137.6	215.1	352.4	550.6
Splitting Bond Stress, $\tau_{sp,d}$	[N/mm ²]	3.91	3.91	3.91	3.63	3.13	3.13	3.13
Drilled Hole Diameter, d_o	[mm]	13 ~ 14	15 ~ 16	20 ~ 22	25 ~ 28	30 ~ 32	40 ~ 42	50 ~ 52
Bar Spacing, s	[mm]	50	60	80	100	125	160	200
Edge Distance, c	[mm]	40	40	40	50	65	80	100
$L_{b,req} / \text{Rebar } \phi$		28	28	28	30	35	35	35
Anchorage Length, L_b [mm]		Design Tensile Pull-Out / Concrete Cone Resistance, N_{rd} [kN]						
100	12.3	"Minimum depth to develop full steel shear"						
120	14.7							
160	19.7							
200	24.6							
250	30.7							
275	33.8							
280	34.4							
320	47.2							
335	49.6							
400	78.6							
450	88.1							
525	119.8							
605	137.6							
750	184.4							
875	215.1							
950	299.0							
1120	352.4							
1300	511.4							
1400	550.6							
Length to Develop Steel Yield, $L_{b,req}$ [mm]		280	336	448	603	875	1,120	1,400

- 1) Design tensile steel resistance: $N_{Rd,s} = f_y * A_s / \gamma_{Ms,N}$ where $\gamma_{Ms,N} = 1.05$ (based on steel yield of 460 N/mm²).
- 2) Design value complied in accordance to BS8110 and ACI 318 concrete splitting criteria.
- 3) Minimum spacing shall be $4d_s$ bar to bar or $5d_s$ centre-to-centre.
- 4) Minimum edge distance shall be $2d_s$ bar to bar or $2.5d_s$ centre-to-centre.
- 5) Applicable to dry and wet concrete application.
- 6) Design value based on non-cracked concrete.

TEST CERTIFICATIONS


- 1) Tested to SIRIM QAS to BS 5950 Part 1 for studs and rebars.

SUGGESTED APPLICATIONS




Overlap joints for slabs and beams or foundation column or wall; rebar connection for simply supported slabs or beams; shear connector or compression component joints.
 Important note: Architect or design engineer must conduct final checked with the actual site condition for any variations against tabulated data.

▶ SETTING DIAGRAM



▶ INSTALLATION PROCEDURE



EPG65 HIGH STRENGTH EPOXY FOR POST-INSTALLED REBAR APPLICATIONS

(Design Load Approach with BS8110 & ACI 318 Concrete Splitting Criteria)

Concrete Compressive Strength: $f_{ck,cube} = 35 \text{ N/mm}^2$


Rebar Size, d_s		$\phi 10$	$\phi 12$	$\phi 16$	$\phi 20$	$\phi 25$	$\phi 32$	$\phi 40$						
Design Steel Resistance, $N_{Rd,s}$	[kN]	34.4	49.6	88.1	137.6	215.1	352.4	550.6						
Splitting Bond Stress, $\tau_{sp,d}$	[N/mm ²]	4.17	4.17	4.17	3.88	3.34	3.34	3.34						
Drilled Hole Diameter, d_o	[mm]	13 ~ 14	15 ~ 16	20 ~ 22	25 ~ 28	30 ~ 32	40 ~ 42	50 ~ 52						
Bar Spacing, s	[mm]	50	60	80	100	125	160	200						
Edge Distance, c	[mm]	40	40	40	50	65	80	100						
$L_{b,reqd} / \text{Rebar } \phi$		26	26	26	28	33	33	33						
Anchorage Length, L_b [mm]		Design Tensile Pull-Out / Concrete Cone Resistance, N_{rd} [kN]												
100	13.1	"Minimum depth to develop full steel shear"												
120	15.7								18.9					
160	21.0								25.2	33.5				
200	26.2								31.4	41.9	48.8			
250	32.8								39.3	52.4	61.0	65.6		
265	34.4								41.7	55.6	64.6	69.5		
300									47.2	62.9	73.1	78.7		
320									49.6	67.1	78.0	84.0	107.5	
375										78.6	91.4	98.4	125.9	
400										88.1	97.5	104.9	134.3	167.9
450											109.7	118.1	151.1	188.9
565											137.6	148.2	189.7	237.2
700												183.6	235.1	293.8
820												215.1	275.4	344.2
900													302.2	377.8
1050													352.4	440.8
1100							461.7							
1200							503.7							
1310							550.6							
Length to Develop Steel Yield, $L_{b,yld}$ [mm]		263	315	420	565	820	1,049	1,312						

- 1) Design tensile steel resistance: $N_{Rd,s} = f_y * A_s / \gamma_{Ms,N}$ where $\gamma_{Ms,N} = 1.05$ (based on steel yield of 460 N/mm²).
- 2) Design value complied in accordance to BS8110 and ACI 318 concrete splitting criteria.
- 3) Minimum spacing shall be $4d_s$ bar to bar or $5d_s$ centre-to-centre.
- 4) Minimum edge distance shall be $2d_s$ bar to bar or $2.5d_s$ centre-to-centre.
- 5) Applicable to dry and wet concrete application.
- 6) Design value based on non-cracked concrete.

TEST CERTIFICATIONS

- 1) Tested to SIRIM QAS to BS 5950 Part 1 for studs and rebars.


SUGGESTED APPLICATIONS



Overlap joints for slabs and beams or foundation column or wall; rebar connection for simply supported slabs or beams; shear connector or compression component joints.

Important note: Architect or design engineer must conduct final checked with the actual site condition for any variations against tabulated data.

▶ SETTING DIAGRAM



▶ INSTALLATION PROCEDURE

